

## Technical Information

INOLUB™ P401F is a free flowing fluoropolymer based powder designed primarily to be incorporated in very low concentrations as a film extrusion processing aid – primarily in LLDPE, mLLDPE and other polyolefins. It is targeted especially at today's modern polyolefin resins, enabling molecular architectures that can meet the ever increasing demands of film performance but without compromising their extrusion capabilities.

## Product Features

- Melt fracture ("shark skin") elimination for high clarity and gloss
- No effect on printability or mechanical strength
- Die build up reduction
- May be used in higher temperature processes (e.g. cast film extrusion)
- Cost savings through improved output and energy reduction
- High efficiency grade—typical effective concentration can be as low as 50ppm
- Lubricates die, enabling lower process pressures and temperatures

## Typical Properties

Properties	Value
Appearance	White free flowing powder
Active component	90 %
Anti-caking Agent	10 %
Bulk Density	900 g/l

Note-These are typical properties and not to be used for specification purposes

## Practical considerations

Due to its low end use concentration, INOLUB™ P401F is recommended to be added in the following ways:

- Polymer manufacture: Direct addition typically in a "one pack" additive blend during pelletisation.
- Masterbatch: Content typically 0.5 - 5% INOLUB™ P401F. Conveniently dosed to achieve the desired level, either in polymer compounding/manufacture or directly in the film extrusion process. See INOLUB™ PPA "Masterbatch Compounding Guide"

## Food Contact Statement

**USFDA**– INOLUB™ P401F may be used as a processing aid at levels not exceeding 0.2% of the fluoropolymer (CASRN 9011-17-0), for all polymers intended for use in contact with all food types as described in Table 1 of 21 C.F.R. 176.170(c) under FDA's Conditions of Use A through H described in Table 2 of 21 C.F.R. 176.170(c).

**EU** – INOLUB™ P401F also complies with Regulation (EC) No 1935/2004 on materials and articles intended to come into contact with food and with Commission Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food.

It is the sole responsibility of the user to determine whether the use of INOLUB™ P401F in a particular application is suitable and complies with applicable laws and regulations.

## Storage

INOLUB™ P401F may be stored indefinitely, provided that the packaging remains unopened and that it has been stored in a clean and dry area at temperatures below 27°C (80°F).

## Safety and Handling

Although INOLUB™ P401F presents no safety hazard under normal handling conditions, please refer to the Material Safety Data Sheet to avoid potential hazards prior to processing.

## Packaging

INOLUB™ P401F is available in 25 Kg PE sacks within a corrugated box.

## Disclaimer

INOLUB™ is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer additive. INOLUB™ can be used in applications duly approved by GFL. Customers who plan to use the word INOLUB™ as the trade mark on or relation to their own articles or other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL product is permitted to claim that their products contain INOLUB™ without prior permission from GFL.

## Note warning

Do not use any of INOLUB™ fluoropolymer additives in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

For more information, please contact Gujarat Fluorochemicals Limited

Corporate & Marketing Office :  
INOX Towers, Plot No.17, Sector 16A  
Noida-202301, U.P., INDIA  
Tel : +91-120-6149600  
Fax : +91-120-6149610

Works :  
12/A, GIDC Dahej Industrial Estate, Tehsil  
Vagra, Distt. Bharuch-392130, Gujarat, INDIA  
Website : [www.gfl.co.in](http://www.gfl.co.in)  
Email : [contact@gfl.co.in](mailto:contact@gfl.co.in)

