

R810F

(Rheology modifier)

TECHNICAL DATA SHEET

TECHNICAL INFORMATION

INOLUB™ R810F is a PTFE micropowder with discrete particles and good powder flow. Viscosity effects are minimized, and migration tendency is also reduced. INOLUB™ R810F is one of our most versatile products and can be used in a wide range of applications as an additive at a concentration in the range of 1-20%.

PRODUCT FEATURES

- Low friction and squeak
- Excellent wear resistance
- Improved stain resistance and soil release
- Improved pressure velocity limits
- FDA/EU compliant
- Discrete particles, providing minimal rheological impact

TYPICAL PROPERTIES

Properties	Test Method	Unit	Nominal Value
Appearance	-	-	White free flowing powder
Bulk density	ASTM D4894	g/l	750
Mean particle size	ASTM D4894	µm	600
Specific surface area	Nitrogen Adsorption	m ² /g	<3
Melting point	ASTM D4894	°C (°F)	342 (648)

Note: These are typical properties and not to be used for specification purposes.

TYPICAL END USE APPLICATIONS

INOLUB™ R810F is a versatile product and can be used as an additive in polymers, coatings, paints, and lubricants. INOLUB™ R810F may also be used in polymers to reduce friction and wear, and to improve non-stick performance.

FDA/EU STATEMENT

INOLUB™ R810F meets the compositional requirement of Food and Drug Administration (FDA) regulation 21C.F.R.177.1550, and EU food contact regulation 10/2011. A detailed statement is available upon request.

INOLUB™ R810F

PACKAGING

INOLUB™ R810F is available in 25 kg corrugated boxes, packed in a polyethylene liner.

STORAGE

INOLUB™ R810F may be stored indefinitely, provided that the packaging remains unopened and that it has been stored in a clean and dry area at temperature below 27°C (80°F).

SAFETY AND HANDLING

Although INOLUB™ R810F presents no safety hazard under normal handling conditions, please refer to the Material Safety Data Sheet to avoid potential hazards before processing.

INOLUB™ is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer additives. INOLUB™ can be used in applications duly approved by GFL. Customers who plan to use the word INOLUB™ as the trademark on or relation to their manufactured parts and other products in any style or combination or any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer additives is permitted to claim that their products contain INOLUB™ without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on the information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and ensure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of the use of this information for application of its INOLUB™ branded fluoropolymer additives and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

WARNING: Do not use any of INOLUB™ PTFE additives in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

SALES AND TECHNICAL SUPPORT

Corporate & Marketing Headquarter

Gujarat Fluorochemicals Limited

INOX Towers, 17, Sector-16A,
Noida - 201301 U.P., India
+91 120 6149600

Europe

Gujarat Fluorochemicals GmbH

Regus Center Watermark 14th Floor,
Überseeallee 10, 20457 Hamburg, Germany
+49 40 808074-667/668

Works

Gujarat Fluorochemicals Limited

12/A Dahej, GIDC, Industrial Estate,
Tehsil Vagra, Dist. Bharuch 392130, Gujarat, India
+91 2641 618003

Americas

GFL Americas, LLC

1212 Corporate Dr., Suite-540,
Irving, TX 75038, USA
+1 512 446 7700

