

WD201F

TECHNICAL DATA SHEET

TECHNICAL INFORMATION

INOLUB® WD201F is a low molecular weight aqueous milky dispersion which consists of very small particles (<0.20 µm) of PTFE resin, stabilized in water by non-ionic surfactant. It is formulated for use in aqueous media.

FEATURES AND BENEFITS

- Low friction and squeak
- Excellent wear resistance
- Improved stain resistance and soil release
- PFOA free
- FDA compliant

PROPERTIES

Properties	Test Method	Unit	Nominal Value
Solid Content (% PTFE resin by weight)	ASTM D4441	%	50
Melt Flow Index of PTFE resin (372°C/2.16 kg/2.095mm)	ASTM D1238	g/10 min	0.5
Specific gravity	ASTM D4441	-	1.51
Average particle size	GFL Internal Method	nm	<200
pH of dispersion	ASTM E70	-	>9.5

Note: These are typical properties and not to be used for specification purposes.

TYPICAL END USE APPLICATIONS

INOLUB® WD201F is advised for a wide variety of applications in coatings and printing ink formulations. It is suitable for thin film applications at a typical level of 1-5% solid by weight to the total formulation.

REACH COMPLIANCE

INOLUB® WD201F does not contain PFOA and PFOS, intentionally or unintentionally, and comply with REACH regulations for POPs as per (EU) 2019/1021 & EU 2020/784.

FDA/EU STATEMENT

INOLUB® WD201F meets the compositional requirement of food contact regulations, US FDA 21 C.F.R.177.1550, and EU 10/2011. A detailed statement is available upon request.

PACKAGING

INOLUB® WD201F is available in 30 litre (7.9 gal) non-returnable plastic drum and 1000 litre (264 gal) IBC recyclable containers.

INOLUB® WD201F

HANDLING AND STORAGE

Aqueous dispersions should be stored at temperatures between 10°C and 25°C. Freezing the dispersion or storage of dispersion at high temperatures must be avoided due to its irreversible coagulating effect on PTFE particles. Aqueous dispersions have a low settling tendency although if the dispersions are to be stored for a long duration, it should be rolled or gently agitated twice a month or before usage to rejuvenate settled particles.

Ammonium hydroxide is used by GFL to maintain the pH of dispersion between 9.5 and 10.5 at the time of shipment. High ambient temperatures can deplete the ammonia level and reduce the pH which favors bacterial growth in dispersion and can cause odor and scum. The pH should be monitored and maintained between 9.5 and 10.5.

Please read our Material handling and Storage guide for more information.

SAFETY AND HANDLING

Although INOLUB® WD201F presents no safety hazard under normal handling conditions, please refer to the Material Safety Data Sheet to avoid potential hazards before processing.

INOLUB® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer additives. INOLUB® can be used in applications duly approved by GFL. Customers who plan to use the word INOLUB® as the trademark on or relation to their manufactured parts and other products in any style or combination or any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer additives is permitted to claim that their products contain INOLUB® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on the information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and ensure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of the use of this information for application of its INOLUB® branded fluoropolymer additives and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

WARNING: Do not use any of INOLUB® PTFE additives in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

SALES AND TECHNICAL SUPPORT

Corporate & Marketing office:

Gujarat Fluorochemicals Limited

Inox Towers, Plot no. 17, Sector 16/A

Noida-202301, U.P., INDIA

Tel: +91-120-6149600

Fax: +91-120-6149610

Europe

Gujarat Fluorochemicals GmbH

Esplanade 40, 9th Floor

20354 Hamburg, Germany

+49 40 5582 395 - 80

Works

Gujarat Fluorochemicals Limited

12/A, GIDC Dahej Industrial Estate.

Tehsil- Vagra, Distt. Bharuch-392230, Gujarat, INDIA

Website: www.fluonox.co.in; www.gfl.co.in

Email: contact@gfl.co.in

Americas

GFL Americas, LLC

1212 Corporate Dr., Suite-540,

Irving, TX 75038, USA

+1 512 446 7700

